

# DRYKOFACHADA

3 in 1 acrylic waterproofing paint



**Packaging**

3.6-kg gallon  
18-kg bucket



**Pallets**

3.6 kg – 36 trays with 4 units = 144 units

18 kg – 36 units

**Finishing**

White

**Consumption**

0.150 to 0.200 kg/m<sup>2</sup>/coat

**Shelf life**

Valid for 24 months from the date on which it was manufactured, as long as the storage regulations are observed.

Store in a covered, dry, ventilated place, away from heat sources, in environments with a temperature not exceeding 30°C and in an upright position.

**Description**

3 in 1 acrylic paint to seal the first coat, waterproofing on the second coat and finishing on the last coat. Waterproofing the surface to protect it from rain and to prevent moisture from getting in.

**Where to apply**

- ✓ Facade;
- ✓ Facade protection for vertical gardens;
- ✓ Rain protection;

For other applications consult our technical team **DRYKO**.

**Advantages**

- ✓ Greater coverage;
- ✓ Application as paint;
- ✓ Non-toxic product;
- ✓ Durable;
- ✓ It can be pigmented, water-based dye and light tones;
- ✓ Low water absorption;

**Technical Data**

Tests	Unit	Specification
Specific Mass	g/cm <sup>3</sup>	1.350 to 1.450
Krebs Stormer Viscosity	KU	100 to 110
Drying between coats	Time	2 to 3

**Surface preparation**

The substrate for the application of **DRYKOFACHADA** must be clean, free of foreign bodies, mold remains, hardware tips, remnants of release or impregnating agents, flaws and niches. On smooth concrete, sand with a steel brush or mechanically to increase porosity and remove release or curing agents.

On surfaces with old paint, sanding must be carried out to remove loose parts. Cracks and fissures must be treated before applying the product.

**Notes**

[www.DRYKO.com.br](http://www.DRYKO.com.br)

DRYKO has it covered!

Rua Antônio Rodrigues Filho, 404 | Vila Aeroporto.  
Guarulhos | SP | Zip Code (CEP) 07170-325  
Phone: 11 2088-5700



# DRYKOFACHADA

3 in 1 acrylic waterproofing paint



The mortar used for leveling must not contain lime and water-repellent additives. Wait for the mortar to cure for at least 7 days.

We recommend not applying the product in rainy weather and wet substrate. We recommend applying the product at temperatures between 10 and 40°C, and humidity below 85%.

### Handling and safety

- ✓ Handle with care.
- ✓ We recommend observing the safety standards established by the competent bodies and the use of appropriate PPE.
- ✓ In case of accidental ingestion, do not force vomiting. In contact with eyes, rinse well with water for at least 15 minutes. In contact with the skin, wash well with soap and water and use a moisturizing cream. See a doctor.
- ✓ Keep out of reach of children and animals.
- ✓ In closed places, if necessary, create forced ventilation.
- ✓ For further information on handling and safety, refer to the product MSDS, available on our website – [www.dryko.com.br](http://www.dryko.com.br).
- ✓ Dispose of content/container at an approved waste treatment plant.

### Application of DRYKOFACHADA

With the product in the original packaging, mix for approximately 2 minutes. Use a roller, a spalter or a brush to apply the product.

While the substrate dry, apply the 1st coat of **DRYKOFACHADA** diluted in 10% water to seal the surface and wait for 2 to 3 hours for it to dry.

Apply the 2nd coat of pure **DRYKOFACHADA** in an even layer without excess to waterproof the surface and wait for 2 to 3 hours for it to dry.

Apply the 3rd coat of pure **DRYKOFACHADA** in an even layer without excess to obtain a white finishing.

**DRYKOFACHADA** must be left exposed and cannot receive mechanical protection or coating.

### Cleaning

Cleaning of tools and equipment can be carried out with water before drying the product, after the drying process the removal must be carried out mechanically.

### LEGAL NOTICE

DRYKO IMPERMEABILIZANTES guarantees the quality of its products against manufacturing defects, according to the legal provisions of the Consumer Protection Code, pointing out that the final performance of the product is directly influenced by the quality of the application and its conditions, including factors such as climate, temperature, storage, and ways of application.

DRYKO may make changes to the products whenever it deems necessary, without prior notice.

The information on this product datasheet is based on our experience and knowledge, for guidance purposes, and in accordance with the procedures of the current standard, with laboratory analyses carried out in accordance with the requirements of the products, uses not provided for in this document will not be considered.

[www.DRYKO.com.br](http://www.DRYKO.com.br)

DRYKO has it covered!

Rua Antônio Rodrigues Filho, 404 | Vila Aeroporto.  
Guarulhos | SP | Zip Code (CEP) 07170-325  
Phone: 11 2088-5700

